



WEAVING YARN

Sley in Reed	Reed Size (dents per cm, dpcm)												
	20/10	25/10	30/10	35/10	40/10	45/10	50/10	55/10	60/10	70/10	80/10	90/10	100/10
0-0-1	0.7	0.9	1	1.2	1.4	1.5	1.7	1.9	2	2.4	2.7	3	3.4
0-1	1	1.3	1.5	1.8	2	2.3	2.5	2.8	3	3.5	4	4.5	5
0-1-1	1.4	1.7	2	2.4	2.7	3	3.4	3.7	4	4.7	5.4	6	6.7
0-1-1-1	1.5	1.9	2.3	2.7	3	3.4	3.8	4.2	4.5	5.3	6	6.8	7.5
1	2	2.5	3	3.5	4	4.5	5	5.5	6	7	8	9	10
1-1-1-2	2.5	3.2	3.8	4.4	5	5.7	6.3	6.9	7.5	8.8	10	11.3	12.5
1-1-2	2.7	3.4	4	4.7	5.4	6	6.7	7.4	8	9.4	10.7	12	13.4
1-2	3	3.8	4.5	5.3	6	6.8	7.5	8.3	9	10.5	12	13.5	15
1-2-2	3.4	4.2	5	5.9	6.7	7.5	8.4	9.2	10	11.7	13.4	15	16.7
1-2-2-2	3.5	4.4	5.3	6.2	7	7.9	8.8	9.7	10.5	12.3	14	15.8	17.5
2	4	5	6	7	8	9	10	11	12	14	16	18	20
2-2-2-3	4.5	5.7	6.8	7.9	9	10.2	11.3	12.4	13.5	15.8	18	20.3	22.5
2-2-3	4.7	5.9	7	8.2	9.4	10.5	11.7	12.9	14	16.4	18.7	21	23.4
2-3	5	6.3	7.5	8.8	10	11.3	12.5	13.8	15	17.5	20	22.5	25
2-3-3	5.4	6.7	8	9.4	10.7	12	13.4	14.7	16	18.7	21.4	24	26.7
2-3-3-3	5.5	6.9	8.3	9.7	11	12.4	13.8	15.2	16.5	19.3	22	24.8	27.5
3	6	7.5	9	10.5	12	13.5	15	16.5	18	21	24	27	30
3-3-3-4	6.5	8.2	9.8	11.4	13	14.7	16.3	17.9	19.5	22.8	26	29.3	32.5
3-3-4	6.7	8.4	10	11.7	13.4	15	16.7	18.4	20	23.4	26.7	30	33.4
3-4	7	8.8	10.5	12.3	14	15.8	17.5	19.3	21	24.5	28	31.5	35
3-4-4	7.4	9.2	11	12.9	14.7	16.5	18.4	20.2	22	25.7	29.4	33	36.7
3-4-4-4	7.5	9.4	11.3	13.2	15	16.9	18.8	20.7	22.5	26.3	30	33.8	37.5
4	8	10	12	14	16	18	20	22	24	28	32	36	40
4-4-4-5	8.5	10.7	12.8	14.9	17	19.2	21.3	23.4	25.5	29.8	34	38.3	42.5
4-4-5	8.7	10.9	13	15.2	17.4	19.5	21.7	23.9	26	30.4	34.7	39	43.4
4-5	9	11.3	13.5	15.8	18	20.3	22.5	24.8	27	31.5	36	40.5	45
4-5-5	9.4	11.7	14	16.4	18.7	21	23.4	25.7	28	32.7	37.4	42	46.7
4-5-5-5	9.5	11.9	14.3	16.7	19	21.4	23.8	26.2	28.5	33.3	38	42.8	47.5
5	10	12.5	15	17.5	20	22.5	25	27.5	30	35	40	45	50



WEAVING **YARN**

How to use the reed substitution table

- (1) Find your reed size in the top row of the table.
- (2) Trace down the column to find the nearest ends per centimetre (epcm) of your desired sett.
- (3) Trace across to the left hand column to see the sleying pattern you need to use.

Note: epcm values are calculated to the next 0.1 epcm. Not all reed substitutions are practical.

Need a reed? Go to weavingyarn.co.uk/reeds